

Bronzepulver bronze powder

| Sorten <i>grades</i> | Bz 94/6 | Bz 90/10 | Bz 85/15 | Bz 80/20 | Bz 60/40 | Bz 50/50 |
|--|--|-------------|-------------|-------------|-------------|-------------|
| Kornform <i>particle shape</i> | spratzig <i>irregular</i> | | | | | |
| Füllichte <i>apparent density (typical values)</i> | 3,3 | 3,3 | 3,3 | 3,3 | 3,3 | 3,3 |
| Chem. Zusammensetzung (%) <i>chemical composition</i> | | | | | | |
| Kupfer <i>copper</i> | 92,5 - 94,0 | 88,5 - 90,5 | 83,5 - 85,5 | 78,5 - 80,5 | | |
| Zinn <i>tin</i> | 5,5 - 7,0 | 9,0 - 11,0 | 14,0 - 16,0 | 19,0 - 21,0 | 38,0 - 42,0 | 48,0 - 52,0 |
| Zink <i>zinc</i> | <=1 | <=1 | <=1 | <=1 | <=1 | <=1 |
| Bronze <i>cut</i> | - 40 WA DT | | | - 63 WA DT | | |
| | 45µ | | | 63µ | | |
| Verpackung <i>packaging</i> | Plastikbeutel oder Metalltrommeln zu je 1 kg, 5 kg, 10 kg, 25 kg plastic bags or metal drums of each 1 kg, 5 kg, 10 kg, 25 kg | | | | | |

Vorstehende Angaben sind technische Qualitätsbeschreibungen und keine zugesicherten Eigenschaften im Rechtssinne

The aforesaid dates are given for purposes of technical quality description only and do not constitute expressed warranties in legal terms.